

FSC® cert. no. C019045
chipped with green ID plug

Values are based on door blanks, dimensions 2350 x 950 mm

thickness (mm.)	thermal conductivity W/(m ² .K)	weight (approx. kg.) and per m ²	shape stability class	sound reduction Rw/C/Ctr (dB)	fire resistance (min.)	KOMO BRL 1705 certified	burglary resistance class
40 mm	1.68	42 / 19	3 (≤2 mm)	34 / 0 / -2	30	SKH 32631-2013	2
44 mm	1.53	47 / 21	3 (≤2 mm)	-	30	SKH 32631-2013	2
54 mm	1.38	58 / 26	3 (≤2 mm)	-	-	SKH 32631-2013	2
56 mm	1.36	60 / 27	3 (≤2 mm)	-	-	SKH 32631-2013	2
68 mm	1.14	71 / 32	3 (≤2 mm)	-	-	SKH 32631-2013	2
76 mm	1.03	80 / 36	3 (≤2 mm)	-	-	SKH 32631-2013	2

Legenda

Thickness	Thickness in mm.
Thermal conductivity	Calculated Up-value (Up = Upanel), according EN-ISO 10077-2
Weight	Weight of the door blank and average weight in kg. per m ²
Shape stability class	Tested according BRL-0803 (NEN-EN 12219 and NEN-EN 1121) and guaranteed by Mill Panel
Sound reduction	According ISO 140-1, 140-2, 140-3 and ISO 717-1
Fire resistance	According EN 1634-1/2008 and in accordance with fire report (on ask)
KOMO BRL 1705	Dutch assessment base for KOMO SKH product certification: Plywood (exterior use)
Burglary resistance class	Resistancy Class-2 according NEN-5096

Rev. juni 2015



wood panel technology

Eerste industrieweg 7
5451 GV Mill
the Netherlands

t 0031 - 485 - 44 24 40
f 0031 - 485 - 31 12 82
e info@millpanel.com
i www.millpanel.com