

FSC® cert. no. C019045  
chipped with red ID plug

Values are based on door blanks, dimensions 2350 x 950 mm

thickness (mm.)	thermal conductivity W/(m <sup>2</sup> .K) U <sub>p</sub> /N <sub>i</sub> /i	weight (approx. kg.) and per m <sup>2</sup>	shape stability class	sound reduction Rw/C/Ctr (dB)	fire resistance (min.)	SKH- BGS-001 certified	burglary resistance class
54 mm	1.08 / 1.82 / 0.80	36 / 16	2 (≤4 mm)	-	45	SKH-024	2

Legenda

- Thickness** Thickness in mm.
- Thermal conductivity** Calculated Up-value (Up = Upanel), according EN-ISO 10077-2  
Up weighted U-value of panel  
Ni U-value of non-insulated part  
i U-value of insulated part
- Weight** Weight of the door blank and average weight in kg. per m<sup>2</sup>
- Shape stability class** Tested according BRL-0803 (NEN-EN 12219 and NEN-EN 1121) and guaranteed by Mill Panel
- Sound reduction** According ISO 140-1, 140-2, 140-3 and ISO 717-1
- Fire resistance** According EN 1634-1/2008 and in accordance with fire report (on ask)
- SKH-BGS-certified** SKH-BeoordelingsGrondSlag (assessment base) regarding exterior door blanks analogous to KOMO-BRL 0803 for exterior timber doors
- Burglary resistance class** Resistancy Class-2 according NEN-5096

Rev. februari 2016



wood panel technology

Eerste industrieweg 7  
5451 GV Mill  
the Netherlands

t 0031 - 485 - 44 24 40  
f 0031 - 485 - 31 12 82  
e info@millpanel.com  
i www.millpanel.com